



BODY 910 UNDERBODY COATING

Technical Data Sheet No 709

General Technical Description

Thixotropic material based on rubber

An excellent coating for corrosion protection with sound-deadening properties and resistance to road stone chipping

It is finely and permanently adhered

Dries quickly and it can be painted- after drying- with all Paint systems

It does not lose its shape with temperature

It does not run and it does not sag on vertical surfaces

Surface

Underbody parts

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is first wiped then air dried.



Make sure you always use appropriate face protection and good ventilation

Product Application:

»» It is applied on the underbody of the car, on the inside of the trunk and on the body floor. Is recommended to be used under the doors, wheels arches, the parts of the car, porte-baggage and to internal ground parts of the car. Dries quickly and it can be painted- after drying- with all Paint systems. Applicable with a brush or a spray gun at a pressure of 5-6 bars



Apply with brush



Drying time
2-6h /23°C (73°F)



Protect from humidity



Always close tin after use



Always wear protective equipment



Follow the application instructions mentioned in this TDS



Always mix well before use



Addition of 10-20% Body 767 ECO Nitro Thinner



Apply with spray gun: 4-5mm Pressure 5-6 bar (73-87psi)

Flash Point:
4°C / 39°F

Specific Gravity:
1.1 g/cm³

Solid Content (No thinner):
63% Weight

VOC (2004/42/EC)
This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in ready for use form of this product is 480 g/L.
2004/42/II(b)(e)(840)480

Theoretical Coverage:
5 - 6 m² / L at 100 micron (4mil) dry film thickness

Cleaning of equipment:
Clean after final use with:
Body 740 ACRYL NORMAL
Body 767 ECO Nitro Thinner

Remarks:

- Allow for additional time for combi spray booths to reach the desired temperature
- Best results when used with HB BODY PRODUCTS.
- It can be used by countries that do not adopt the VOC legislation as well.

Storage shelf life:

- Store in a cool place +5°C - 25°C (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers.

This is a thixotropic material based on rubber. It is applied on the underbody of the car, on the inside of the trunk and on the body floor. Is recommended to be used under the doors, wheels arches, the parts of the car, porte-baggage and to internal ground parts of the car. It offers corrosion protection with sound-deadening properties and resistance to road stone chipping. It remains elastic and it is adhered perfectly. It dries quickly and it can be painted- after drying- with all Paint systems. It can be applied with either a brush or a spray gun at 5-6 bar pressure, over surfaces which have been cleaned from oils, rust and dirt previously. Previous bituminous coatings and layers of wax should be removed.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 4/2018, June 2018